

Substance Scheme

Thermolysis Carbon

Product name: Thermolysis Carbon

Precursor: Tyre rubber

Production process: Pyrum-Thermolysis

Author	Dipl.-Chem. David Hafner	Issued	01/08/2018
Doc.-No.	904	Version	5
Page count	9	© 2018 Pyrum Innovations AG	
Revision index	Date	Description	
Version 1	17/07/2017	First draft of substance scheme	
Version 2	23/08/2017	Addition inner surface	
Version 3	25/09/2017	H+P statements	
Version 4	16/10/2017	Safety parameters	
Version 5	01/08/2018	Addition minimum ignition energy and ignition temperature	

Substance Scheme

Thermolysis Carbon



Table of contents

1	Safety information.....	3
2	Physical Properties.....	4
3	Chemical Properties.....	4
4	Physiological Properties.....	5
5	Composition.....	5
5.1	Single substances and molecules.....	5
5.2	Nuclear Composition.....	5
5.3	Composition of ash.....	6
5.4	Impurity.....	6
6	Safety parameters of grinding thermolysis carbon.....	7
7	Structure.....	8
8	Examples of application (to be completed).....	8
9	Hazard and precautionary statements.....	8
9.1	Relevant hazard warnings.....	8
9.2	Relevant precautionary information.....	8

Substance Scheme Thermolysis Carbon



1 Safety information

Table 1: Relevant hazard notes for packaging and safety data sheet according to GHS

H400; H410	H315		

Precautionary Statements: P273; P501

Table 2: Recommended personal protection equipment

PPE - long clothing	Safety shoes	Breathing protection	Resistant gloves
Safety goggles			

Substance Scheme

Thermolysis Carbon



Table 3: Relevant warning signals and prohibitions for technical applications

			
No open flames	Danger of explosive atmosphere		

Dangerous goods ADR/RID/ADN 3077 ENVIRONMENTALLY HAZARDOUS SUBSTANCE, SOLID, N.O.S. (zinc oxide)

All safety information is based on experience and is merely intended to assist and sensitize the user. It does not replace the user's risk and danger assessment in any way.

2 Physical Properties

state of aggregation:	solid	
colour:	black, grey	
calorific value:	23000-30000 kJ/kg (dry)	
particle density:	900-1100 kg/m ³	ASTM D 1513-05
bulk density:	300-500 kg/m ³	
iodine number:	114,5 +-1 g/kg	ASTN D 1510-13
solubility:	non soluble	
wettability:	low	
dust accumulation:	Dust accumulation with air can result in explosive mixtures.	
BET:	55 m ² /g	
BET after activation:	480-525 m ² /g	

3 Chemical Properties

Sulfuric components can be dissolved by abundant humidity. To be regarded concerning the choice of materials in contact with thermolysis carbon. Slow proceeding corrosion is possible.

Substance Scheme

Thermolysis Carbon



4 Physiological Properties

smell: characteristic, slightly sulfuric

toxicity: see safety data sheet

5 Composition

The values represent a measured maximum, if not specified differently.

5.1 Single substances and molecules

Water content: 0,9 wt.-% DIN ISO 11465

5.2 Nuclear Composition

C: 75-85 wt.-% DIN EN 15104

H: 0,19-0,45 wt.-% DIN EN 15104

N: 0,27-0,36 wt.-% DIN EN 15104

O: n.b.

S: 17000-25000 mg/kg TR DIN EN ISO 10304

Substance Scheme

Thermolysis Carbon



5.3 Composition of ash

By ash we refer to the mixture of all non-volatile substances contained within the solid product, which is not actually carbon. The ash content varies between 15 - 25 wt.-% (DIN 51718 u. DIN 51719).

Table 4: Composition of ash (DIN 51718 u. DIN 51719)

	Content in TC in wt.-%	Content in Ash in wt.-%
SiO ₂	3 to 17	30 to 79
ZnO	2,86 to 5	13 to 50
CaO	0,22 to 1,1	1 to 5
SO ₃	0,22 to 1,1	1 to 5
Al ₂ O ₃	0,22 to 1,1	1 to 5
MgO	0,11 to 0,22	0,5 to 2
K ₂ O	0,11 to 0,22	0,5 to 1
Fe ₂ O ₃	0,11 to 0,6	0,5 to 6
P ₂ O ₅	0,022 to 0,11	0,1 to 1
Co ₂ O ₃	0,022 to 0,11	0,1 to 0,5
TiO ₂	0,022 to 0,11	0,1 to 0,5

5.4 Impurity

Water: low hygroscopicity, humidity can vary

Ash: Ash content varies between 15 - 25 wt.-%, can be recovered as valuable product.

Substance Scheme

Thermolysis Carbon



6 Safety parameters of grinding thermolysis carbon

Table 5: Characteristics of ginded carbon


Method	Norm	Test result				
Humidity	-	1.54 mass % at 70°C				
Smoldering temperature	EN 50281-2-1/ VDI 2263, sheet 1	380 °C				
Calorific factor	VDI 2263, sheet 1	BZ3				
Explosion characteristics	DIN EN 14034/ 1+2	Max. explosion pressure (Pmax)			6.5 bar	
		Max. rate of pressure rise (dP/dt)			144 bar/s	
		Product specific constant (K _{St})			39 bar*m/s	
Lower explosion limit	DIN EN 14034-3 and 14034/ A1, sheet 1	90 g/m ³				
Volume resistance	IEC 60079/32 1+2 and TRGS 727	5*10 ⁴ Ωm The specific resistance of the sample is low (<10 ⁶ Ωm).				
Sieve analysis*	DIN 66 165/ 1+2	Average value		49 μm		
		Mean particle diameter		57 μm		
		0 - 63 μm	63 - 125 μm	125 - 250 μm	250 - 500 μm	> 500 μm
		73.4 %	22.2 %	4.4%	0.0 %	0.0 %
Minimum ignition energy	DIN EN 13821	1000 mJ				
Ignition temperature	DIN EN 50 281-1-2 and VDI 2263, sheet 1	> 600 °C				

Substance Scheme

Thermolysis Carbon

7 Structure

Table 6: REM-shots of thermolysis carbon



8 Examples of application (to be completed)

Filler for production of rubber

Carbon black substitute

Fuel for power generation

9 Hazard and precautionary statements

9.1 Relevant hazard warnings

- H315 Causes skin irritation.
- H400 Very toxic to aquatic life with long lasting effects.
- H410 Toxic to aquatic life with long lasting effects.

9.2 Relevant precautionary information

- P273 Avoid release to the environment.
- P501 Dispose of contents/container to waste disposal facility.